

View Online at <https://aerobasegroup.com/nsn/9535-00-900-1225>

Fabrication Method:

Rolled

Length:

8.000 feet

Cross-sectional Thickness:

0.0120 inches

Basic Shape Style:

Solid

Edge Type:

Square

Min. Tensile Strength (psi):

55000 pounds per square inch

Heat Treatment:

Half hard

Material:

Copper alloy 342 or copper alloy 353

Material Specification:

Qq-b-613, alloy 342 federal specification 1st material response and qq-b-613, alloy 353 federal specification 2nd material response

Specification Or Standard:

342 composition or 353 composition and strip form and half-hard temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100