

View Online at <https://aerobasegroup.com/nsn/9535-00-900-1225>

**Fabrication Method:**

Rolled

**Length:**

8.000 feet

**Cross-sectional Thickness:**

0.0120 inches

**Basic Shape Style:**

Solid

**Edge Type:**

Square

**Min. Tensile Strength (psi):**

55000 pounds per square inch

**Heat Treatment:**

Half hard

**Material:**

Copper alloy 342 or copper alloy 353

**Material Specification:**

Qq-b-613, alloy 342 federal specification 1st material response and qq-b-613, alloy 353 federal specification 2nd material response

**Specification Or Standard:**

342 composition or 353 composition and strip form and half-hard temper

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100