

View Online at <https://aerobasegroup.com/nsn/9535-00-961-0832>

Fabrication Method:

Hot rolled

Width:

50.000 inches

Length:

4.200 feet

Cross-sectional Thickness:

0.0125 inches

Basic Shape Style:

Solid

Leveling Method:

Roller

Min. Tensile Strength (psi):

30000 pounds per square inch

Heat Treatment:

Annealed

Material:

Copper, qq-c-576

Material:

Copper alloy 130

Material Specification:

Qq-c-576 federal specification 1st material response

Specification Or Standard:

Sheet form and hot-rolled and annealed temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100