

View Online at <https://aerobasegroup.com/nsn/9535-01-003-4330>

Fabrication Method:

Cold rolled

Cross-sectional Thickness:

0.0400 inches

Basic Shape Style:

Solid

Heat Treatment:

Solution treated

Material:

Copper, qq-c-533, alloy 172

Material:

Copper alloy 172

Material Specification:

Qq-c-533, alloy 172 federal specification 1st material response

Specification Or Standard:

A condition

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100