

View Online at <https://aerobasegroup.com/nsn/9535-01-010-9557>

Fabrication Method:

Rolled

Cross-sectional Thickness:

0.0630 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Min. Tensile Strength (psi):

42000 pounds per square inch

Minimum Yield Strength:

35000 pounds per square inch

Heat Treatment:

T-1 solution heat treated and artificially aged

Material:

Aluminum alloy, qq-a-250/11, alloy 6061

Material:

Aluminum alloy, qq-a-250/11, alloy 6061

Surface Condition:

Any acceptable

Specification Or Standard:

6 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100