

View Online at <https://aerobasegroup.com/nsn/9535-01-011-9301>

**Fabrication Method:**

Rolled

**Cross-sectional Thickness:**

0.0250 inches

**Basic Shape Style:**

Solid

**Edge Type:**

Any acceptable

**Cladding Thickness:**

0.001 inches both sides

**Min. Tensile Strength (psi):**

70000 pounds per square inch

**Minimum Yield Strength:**

60000 pounds per square inch

**Heat Treatment:**

T-1 solution heat treated and artificially aged

**Material:**

Aluminum alloy, qq-a-250/13, alloy alclad 7075

**Specification Or Standard:**

6 temper

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100