

View Online at <https://aerobasegroup.com/nsn/9535-01-011-9304>

Fabrication Method:

Rolled

Cross-sectional Thickness:

0.0630 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Cladding Thickness:

0.002 inches both sides

Min. Tensile Strength (psi):

73000 pounds per square inch

Minimum Yield Strength:

63000 pounds per square inch

Heat Treatment:

T-1 solution heat treated and artificially aged

Material:

Aluminum alloy, qq-a-250/13, alloy alclad 7075

Specification Or Standard:

6 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100