

View Online at <https://aerobasegroup.com/nsn/9535-01-013-9843>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

8.000 feet

Cross-sectional Thickness:

0.0320 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Cladding Thickness:

0.00128 inches both sides

Min. Tensile Strength (psi):

70000 pounds per square inch

Minimum Yield Strength:

60000 pounds per square inch

Heat Treatment:

T-6 solution heat treated

Material:

Aluminum alloy, ams-qq-a-250/13, alloy 7075

Material:

Aluminum alloy, ams-qq-a-250/13, alloy 7075

Specification Or Standard:

Alloy 7075 and temper t6

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100