

View Online at <https://aerobasegroup.com/nsn/9535-01-014-6664>

Fabrication Method:

Rolled

Cross-sectional Thickness:

0.0200 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Cladding Thickness:

0.001 inches both sides

Min. Tensile Strength (psi):

70000 pounds per square inch

Minimum Yield Strength:

60000 pounds per square inch

Heat Treatment:

T-1 solution heat treated and artificially aged

Material:

Aluminum alloy, qq-a-250/13, alloy alclad 7075

Specification Or Standard:

6 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100