

View Online at <https://aerobasegroup.com/nsn/9535-01-202-3874>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

12.000 feet

Cross-sectional Thickness:

0.1000 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Cladding Thickness:

0.0025 inches both sides

Min. Tensile Strength (psi):

61000 pounds per square inch

Minimum Yield Strength:

38000 pounds per square inch

Heat Treatment:

T-4 solution heat treated

Material:

Aluminum alloy, qq-a-250/5

Material:

Aluminum alloy 2024

Material Specification:

Qq-a-250/5 federal specification 1st material response

Specification Or Standard:

T4 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100