

View Online at <https://aerobasegroup.com/nsn/9535-01-260-6446>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

14.000 feet

Cross-sectional Thickness:

0.1000 inches

Basic Shape Style:

Solid

Cladding Thickness:

0.002 inches both sides

Min. Tensile Strength (psi):

67000 pounds per square inch

Minimum Yield Strength:

57000 pounds per square inch

Material:

Aluminum alloy, alloy 7475, alclad, stm07-120, lockheed corp

Material:

Aluminum alloy, alloy 7475, alclad, stm07-120, lockheed corp

Specification Or Standard:

T761 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100