

View Online at <https://aerobasegroup.com/nsn/9535-01-324-1166>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

144.000 inches

Cross-sectional Thickness:

0.0400 inches

Basic Shape Style:

Solid

Cladding Thickness:

0.0016 inches both sides

Min. Tensile Strength (psi):

67000 pounds per square inch

Minimum Yield Strength:

56000 pounds per square inch

Heat Treatment:

T-76 solution heat treated

Material:

Aluminum alloy, qq-a-250/25, alloy 7075

Material:

Aluminum alloy, qq-a-250/25, alloy 7075

Specification Data:

81343-ams 4316 professional/industrial association standard

Specification Or Standard:

T76 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100