

View Online at <https://aerobasegroup.com/nsn/9535-01-347-7408>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

8.000 feet

Cross-sectional Thickness:

0.0500 inches

Basic Shape Style:

Solid

Cladding Thickness:

0.002 inches both sides

Min. Tensile Strength (psi):

57000 pounds per square inch

Minimum Yield Strength:

34000 pounds per square inch

Heat Treatment:

Annealed

Material:

Aluminum alloy, ams-qq-a-250/5, alloy 2024 (alclad)

Material:

Aluminum alloy, ams-qq-a-250/5, alloy 2024 (alclad)

Specification Or Standard:

Alclad 2024 and condition annealed

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100