

View Online at <https://aerobasegroup.com/nsn/9535-01-351-5326>

Fabrication Method:

Rolled

Width:

0.025 inches

Length:

0.040 inches

Cross-sectional Thickness:

0.0050 inches

Cross-sectional Width:

0.025 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Min. Tensile Strength (psi):

Not rated

Minimum Yield Strength:

Not rated

Special Features:

Clad with gold 99.99 percent pure; 100 microinch min thick both sides (finish on edges optional) and package in quantities not more than 500 pieces per container; one part number per container

Heat Treatment:

Annealed

Material:

Iron 53 percent; nickel 29 percent; cobalt 17 percent; manganese 0.50 percent; silicon 0.20 percent; carbon 0.02 percent

Material:

Iron 53 percent; nickel 29 percent; cobalt 17 percent; manganese 0.50 percent; silicon 0.20 percent; carbon 0.02 percent

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100