

View Online at <https://aerobasegroup.com/nsn/9535-01-517-7134>

Fabrication Method:

Rolled

Cross-sectional Thickness:

0.1000 inches

End Application:

Tornado, mlu, wing, alenia aeronautica spa

Basic Shape Style:

Solid

Min. Tensile Strength (psi):

61000 pounds per square inch

Minimum Yield Strength:

38000 pounds per square inch

Material:

Aluminum alloy 2024

Material Specification:

Qq-a-250/5 federal specification 1st material response

Specification Or Standard:

T4 temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100