

View Online at <https://aerobasegroup.com/nsn/9535-01-563-1179>

**Fabrication Method:**

Rolled

**Basic Shape Style:**

Solid

**Cladding Thickness:**

2.500 inches both sides

**Min. Tensile Strength (psi):**

61000 pounds per square inch

**Minimum Yield Strength:**

38000 pounds per square inch

**Heat Treatment:**

T-81 solution heat treated

**Material:**

Aluminum alloy, qq-a-250/5

**Material:**

Aluminum alloy 2024

**Material Specification:**

Qq-a-250/5 federal specification 1st material response

**Specification Or Standard:**

T81 temper

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100