

View Online at <https://aerobasegroup.com/nsn/9535-01-572-5075>

Fabrication Method:

Cold rolled or hot rolled

Cross-sectional Thickness:

0.005 inches

Min. Tensile Strength (psi):

75000 pounds per square inch

Material:

Copper, qq-c-533, alloy 172

Material:

Copper alloy 172

Material Specification:

Qq-c-533, alloy 172 federal specification 1st material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100