

View Online at <https://aerobasegroup.com/nsn/9535-01-625-4148>

Cladding Thickness:

0.500 inches

Special Features:

Plate is solution heat treat; stretched; precipitation heat treat; contains 4.4 copper; 1.5 magnesium; 0.60 manganese

Heat Treatment:

T-851 solution heat treated and solution treated and stress relieved by stretching

Material:

Aluminum alloy, qq-a-250/29, alloy 2124

Specification Data:

81343-ams-qq-a-250/29/superseded/use ams4101 national std/spec

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100