## NSN 9540-01-032-4191

Structural Beam - Page 1 of 2



View Online at https://aerobasegroup.com/nsn/9540-01-032-4191

**Fabrication Method:** 

Extruded

**Overall Height:** 

Between 1.609 inches and 1.641 inches

Length:

12.000 feet

Left Side Top Flange Thickness:

Between 0.149 inches and 0.163 inches

**Right Side Top Flange Thickness:** 

Between 0.149 inches and 0.163 inches

**Basic Shape Style:** 

T shape

Leg Thickness:

Between 0.149 inches and 0.163 inches

**Usage Design:** 

Structural

Left Side Top Flange Distance To Center Of Both Flanges:

Between 0.805 inches and 0.820 inches

**Right Side Top Flange Distance To Center Of Both Flanges:** 

Between 0.805 inches and 0.820 inches

Fillet Radius Where Top Left Flange Joins Web Flange/leg:

Between 0.109 inches and 0.141 inches

Fillet Radius Where Top Right Flange Joins Web Flange/leg:

Between 0.109 inches and 0.141 inches

**Top Flange Width:** 

Between 1.609 inches and 1.641 inches

Weight Per Unit Measure:

0.488 pounds per linear foot

First Tip Style:

Square w/ inner and outer corner radii

First Tip Inner Radius:

Between 0.016 inches and 0.048 inches

First Tip Outer Radius:

Between 0.016 inches and 0.048 inches

Second Tip Relationship To First Tip:

Identical

Third Tip Relationship To Preceding Tips:

Identical w/first tip

**Right Top Inside Angle:** 

90.0 degrees

**Left Top Inside Angle:** 

90.0 degrees

## **NSN 9540-01-032-4191** Structural Beam - Page 2 of 2



Heat Treatment:
Stress relieved
Material:
Aluminum alloy, qq-a-200/3
Material:
Aluminum alloy 2024
Material Specification:
Qq-a-200/3 federal specification 1st material response
Supplementary Features:
Procured in a qq-a-200/3 basic temper /t3/ and subsequently solution heat treated by user to precipitation heat treat stress-relieved t6 temper
designation mil-h-6088 table vit
Specification Data:
98897-ls1074 manufacturers standard
Shelf Life:
N/a
Unit Of Measure:
<del></del>
Demilitarization:
No
Fiig:
A13100