

View Online at <https://aerobasegroup.com/nsn/9540-01-213-4404>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

Heat Treatment:

T-6511 solution heat treated

Material:

Aluminum alloy ams-qq-a-200/8, alloy 6061

Material:

Aluminum alloy ams-qq-a-200/8, alloy 6061

Specification Data:

76301-1ma10478 manufacturers standard

Specification Or Standard:

T6511 temper

Reference Number Differentiating Characteristics:

As differentiated by length

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100