

View Online at <https://aerobasegroup.com/nsn/9540-01-264-8580>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

Special Features:

C-130 acft

Heat Treatment:

T-6511 solution heat treated

Material:

Aluminum alloy ams-qq-a-200/11, alloy 7075

Material:

Aluminum alloy ams-qq-a-200/11, alloy 7075

Specification Or Standard:

Alloy 7075 and temper t6511

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A13100