

View Online at <https://aerobasegroup.com/nsn/9540-01-298-6999>

**Fabrication Method:**

Extruded

**Overall Width:**

0.375 inches

**Length:**

16.000 feet

**Left Side Flange Height:**

0.938 inches

**Right Side Flange Height:**

0.938 inches

**Left Side Flange Thickness:**

0.093 inches

**Right Side Flange Thickness:**

0.093 inches

**Basic Shape Style:**

Channel

**Base Flange Thickness:**

0.313 inches

**First Tip Style:**

Square w/ inner and outer corner radii

**First Tip Inner Radius:**

0.020 inches

**First Tip Outer Radius:**

0.020 inches

**Second Tip Relationship To First Tip:**

Identical

**Left Inside Angle:**

90.0 degrees

**Right Inside Angle:**

90.0 degrees

**Special Features:**

Ioutside flange 0.200 in. H, ctr along base lg, tapered 13.0667 degrees fm pt 0.087 in. Fm ea edge along lg; tensil strength 22000 psi min, 30000 psi max; hardness webster scale 8.0 min, 11.0 max; dp matte fin.

**Heat Treatment:**

T-52 solution heat treated

**Material:**

Aluminum alloy, qq-a-200/9

**Material:**

Aluminum alloy 6063

**Surface Treatment:**

Anodize

**Surface Treatment:**

Anodized

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100