

View Online at <https://aerobasegroup.com/nsn/9540-01-336-5497>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

End Application:

C-5b aircraft

Usage Design:

Aircraft

Heat Treatment:

T-6511 solution heat treated

Material:

Aluminum alloy ams-qq-a-200/8, alloy 6061

Material:

Aluminum alloy ams-qq-a-200/8, alloy 6061

Specification Or Standard:

T6511 temper

Reference Number Differentiating Characteristics:

By temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100