

View Online at <https://aerobasegroup.com/nsn/9540-01-343-3280>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

End Application:

C-5b acft

Heat Treatment:

T-3511 solution heat treated

Material:

Aluminum alloy ams-qq-a-200/3, alloy 2024

Material:

Aluminum alloy ams-qq-a-200/3, alloy 2024

Specification Or Standard:

T3511 temper

Reference Number Differentiating Characteristics:

By temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fig:

A13100