

View Online at <https://aerobasegroup.com/nsn/9540-01-352-1234>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

End Application:

C-5b acft

Heat Treatment:

T-6 solution heat treated

Material:

Aluminum alloy ams-qq-a-200/11, alloy 7075

Material:

Aluminum alloy ams-qq-a-200/11, alloy 7075

Specification Or Standard:

Alloy 7075 and temper t6

Reference Number Differentiating Characteristics:

By temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100