

View Online at <https://aerobasegroup.com/nsn/9540-01-367-1976>

Fabrication Method:

Extruded

Length:

Between 10.000 feet and 12.000 feet

Heat Treatment:

O-annealed

Material:

Aluminum alloy ams-qq-a-200/3, alloy 2024

Material:

Aluminum alloy ams-qq-a-200/3, alloy 2024

Specification Or Standard:

Alloy 2024 and condition annealed

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100