NSN 9630-00-267-3235

Ferromolybdenum Alloying Additive - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9630-00-267-3235

Physical Form:
Lump
Composition And Percentage:
60.00 by volume molybdenum
Impurities Limitation In Percent:
Carbon 0.10 maximum and copper 1.00 maximum and phosphorous 0.05 maximum and silicon 1.00 maximum and sulphur 0.15 max
Shelf Life:
N/a
Unit Of Measure:

Demilitarization:
No
Fiig:
T094-a