NSN 9630-00-267-4154

Ferromanganese Alloying Additive - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9630-00-267-4154

| Physical Form: |
|--|
| Lump |
| Composition And Percentage: |
| 78.00 by volume manganese and 82.00 by volume manganese and 8.85 by volume iron |
| Impurities Limitation In Percent: |
| Carbon 7.5 maximum and phosphor ous 0.35 maximum and silicon 1.25 maximum and sulphur 0.05 max |
| Specification Or Standard: |
| B grade |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| No |
| Fiig: |
| T094-a |