NSN 9630-00-267-4155

Ferromanganese Alloying Additive - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9630-00-267-4155

Physical Form:
Lump
Composition And Percentage:
80.00 by volume manganese and 85.00 by volume manganese
Impurities Limitation In Percent:
Carbon 1.5 pct max, phosphorus 0.30 pct max, silicon 1.0 pct maximum and sulphur 0.020 pct max
Specification Or Standard:
A, medium carbon grade
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
T094-a