## NSN 9630-00-267-4162

Ferrosilicon Alloying Additive - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9630-00-267-4162

Physical Form:
Slab
Composition And Percentage:
47.00 by volume silicon and 52.00 by volume silicon and 47.76 by volume iron
Impurities Limitation In Percent:
Carbon 0.15 maximum and phosphorous 0.05 maximum and sulphur 0.04 max
Specification Or Standard:
E grade
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
T094-a