## NSN 9650-00-269-1675

High-strength Yellow Brass Ingot - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9650-00-269-1675

## **Composition And Percentage:**

0.70 by volume aluminum and 1.00 by volume aluminum and 56.00 by volume copper and 61.00 by volume copper and 0.40 by volume iron and 2.00 by volume iron and 38.00 by volume zinc and 40.00 by volume zinc

## **Impurities Limitation In Percent:**

Manganese 1.50 maximum and tin 1.00 maximum and lead 0.30 maximum and nickel 0.50 max

## **Specification Or Standard:**

F alloy

Shelf Life:

N/a

**Unit Of Measure:** 

--

**Demilitarization:** 

No

Fiig:

T094-a