NSN 9650-00-269-1675

High-strength Yellow Brass Ingot - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9650-00-269-1675

Composition And Percentage:

0.70 by volume aluminum and 1.00 by volume aluminum and 56.00 by volume copper and 61.00 by volume copper and 0.40 by volume

iron and 2.00 by volume iron and 38.00 by volume zinc and 40.00 by volume zinc

Impurities Limitation In Percent:

Manganese 1.50 maximum and tin 1.00 maximum and lead 0.30 maximum and nickel 0.50 max

Specification Or Standard:

F alloy

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

No

Fiig:

T094-a