

View Online at <https://aerobasegroup.com/nsn/9650-01-301-5245>

Composition And Percentage:

91.30 by volume aluminum and 6.50 by volume silicon and 7.50 by volume silicon and 0.12 by volume iron and 0.25 by volume iron and 0.30 by volume magnesium and 0.40 by volume magnesium

Impurities Limitation In Percent:

Copper 0.10 max; manganese 0.05 max; zinc 0.05 max; titanium 0.20 max; other elements 0.15 max, total, 0.05 maximum ea

Specification Or Standard:

356.2 alloy

Departure From Cited Document:

As modified by mercury free clause

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T094-a